

(19)



Eur päis hes Patentamt  
Eur p an Pat nt Office  
Office europ ´ n des brev ts



(11)

**EP 1 113 517 A2**

(12)

**EUROPEAN PATENT APPLICATION**

(43) Date of publication:  
**04.07.2001 Bulletin 2001/27**

(51) Int Cl.7: **H01M 8/10, H01B 1/12,  
C08F 8/36**

(21) Application number: **00128267.2**

(22) Date of filing: **22.12.2000**

(84) Designated Contracting States:  
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU  
MC NL PT SE TR**  
Designated Extension States:  
**AL LT LV MK RO SI**

(30) Priority: **27.12.1999 JP 37068999  
07.03.2000 JP 2000061768**

(71) Applicant: **Sumitomo Chemical Company,  
Limited  
Chuo-ku Osaka 541-8550 (JP)**

(72) Inventors:  
• **Terahara, Atsushi  
Tsukuba-shi, Ibaraki (JP)**  
• **Iwasaki, Katsuhiko  
Tsukuba-shi, Ibaraki (JP)**  
• **Ikeda, Takashi  
Tsukuba-shi, Ibaraki (JP)**

(74) Representative: **Henkel, Feiler, Hänzeli  
Möhlstrasse 37  
81675 München (DE)**

(54) **Polymer electrolyte and method for producing the same**

(57) Provided is a polymer electrolyte containing a block copolymer comprising one or more blocks having sulfonic acid groups and one or more blocks having substantially no sulfonic acid group, and at least one block among all blocks is a block having aromatic rings in the

main chain thereof, and a method for producing the same. The polymer electrolyte is suitable for a proton conductive film of a fuel cell due to excellent water resistance and heat resistance, and high proton conductivity.

EP 1 113 517 A2

**Description****BACKGROUND OF THE INVENTION**5 **Field of the Invention**

**[0001]** The present invention relates to a polymer electrolyte, particularly, a polymer electrolyte suitably used for a fuel cell and a method for producing the same.

10 **Description of the Related Art**

**[0002]** As a proton conductive polymer electrolyte used in a solid polymer-type fuel cell, perfluorosulfonic acid-based materials typically including Nafion (trade mark of Dupont) are mainly used conventionally because of their excellent property as a fuel cell.

15 **[0003]** However, this material is very expensive which is believed to be a serious problem in wide-spreading a powder generation system using a fuel cell in the future.

**[0004]** Under such circumstances, there are recently activating developments of cheap polymer electrolytes which can replace the perfluorosulfonic acid-based materials. Among others, materials obtained by introducing sulfonic acid groups into an aromatic polyether which is excellent in heat resistance and has high film strength are recognized as hopeful, and for example, JP-A (Kohyo publication) No. 11-502249 describes a sulfonated polyether ketone-based  
20 polymer electrolyte, and JP-A Nos. 10-45913 and 10-21943 describe a sulfonated polyether sulfone-based polymer electrolyte.

**[0005]** In these materials, when the amount of introduced sulfonic acid group is larger, proton conductivity increases generally, however, water absorption of a polymer tends to increase simultaneously. When a film produced from a  
25 polymer having high water absorption property is used in a fuel cell, water produced in using the cell causes large dimension change and reduction in strength.

**[0006]** On the other hand, JP-A (Kohyo publication) No. 10-503788 describes a polymer electrolyte obtained by introducing sulfonic acid groups into a styrene(ethylene-butylene)-styrene triblock copolymer. There is a fear of low heat resistance of this block copolymer since the main chain of the copolymer is flexible.

30

**SUMMARY OF THE INVENTION**

**[0007]** An object of the present invention is to provide a novel polymer electrolyte excellent in water resistance, having high heat resistance, and suitable for a proton conductive film of a cheap fuel cell, and a method for producing  
35 the same.

**[0008]** The present inventors have intensively studied for attaining the above-mentioned object, and resultantly, found that a polymer electrolyte containing a block copolymer having a specific combination of blocks has an excellent property as a proton conductive film for a fuel cell, and completed the present invention.

**[0009]** Namely, the present invention relates to (1) a polymer electrolyte containing a block copolymer comprising  
40 one or more blocks having sulfonic acid groups and one or more blocks having substantially no sulfonic acid group, and at least one block among all blocks is a block having aromatic rings in the main chain thereof. Also, the present invention relates to (2) a method for producing a polymer electrolyte of (1), comprising the steps of reacting a precursor of a block having a repeating unit represented by below described general formula [1], [2] or [3] with a precursor of a block having a repeating unit represented by the general formula [4] to produce a block copolymer, and then sulfonating  
45 the copolymer. Further, the present invention relates to (3) a fuel cell obtained by using a polymer electrolyte of (1).

**DETAILED DESCRIPTION OF THE INVENTION**

**[0010]** The polymer electrolyte of the present invention contains a block copolymer comprising one or more blocks  
50 having sulfonic acid groups and one or more blocks having substantially no sulfonic acid group, and in which at least one block among all the blocks is a block having aromatic rings in the main chain thereof.

**[0011]** In the present invention, the term block means a polymer in which two or more units of the same kind of repeating units are connected. The term block copolymer means a polymer in which two or more blocks are directly bonded or bonded via a connecting group, namely, a polymer comprising a plurality of blocks composed of two kinds  
55 or more repeating units.

**[0012]** In the present invention, the term block containing sulfonic acid groups means a block in which 0.5 or more in average of sulfonic acid groups (represented by  $\text{-SO}_3\text{H}$ ) are bonded to one repeating unit constituting a block, at any portion of the repeating unit.


[0013] Bonding form of the sulfonic acid groups to repeating units constituting a block is not particularly restricted, and a structure in which sulfonic acid groups are directly bonded to aromatic rings is preferable since synthesis thereof is relatively easy.

[0014] On the other hand, in the present invention, the term block containing substantially no sulfonic acid group means a block in which the introduced amount of sulfonic acid group is 0.1 or less in average per one repeating unit constituting a block.

[0015] In the present invention, the block having aromatic rings in the main chain thereof may be a block containing sulfonic acid groups, a block containing substantially no sulfonic acid group, or both of them.

[0016] In the present invention, examples of the block containing sulfonic acid groups include blocks obtained by introducing sulfonic acid groups into blocks composed of polystyrene, poly( $\alpha$ -methylstyrene), poly(allyl phenyl ether), poly(phenyl glycidyl ether), poly(phenylene ether), polyphenylene sulfide, polyether ether ketone, polyether ether sulfone, polysulfone, poly(phenylmethylsiloxane), poly(diphenylsiloxane), poly(phenylmethylphosphazene), poly(diphenylphosphazene), epoxy resins and the like.

[0017] Among them, blocks obtained by introducing sulfonic acid groups into a block having a repeating unit represented by the general formula [1], a block having a repeating unit represented by the general formula [2], or a block composed of an epoxy resin, are preferably used.




In the formula [1], X represents -O-, -S-, -NH- or direct bond, R<sup>1</sup> represents an alkyl group having 1 to 6 carbon atoms, an alkoxy group having 1 to 6 carbon atoms or a phenyl group, and a is an integer from 0 to 3. When a plurality of R<sup>1</sup>s are present, these may be the same or different.

[0018] Examples of the block having a repeating unit represented by the general formula [1] include poly(phenylene), poly(aniline), poly(phenylene ether), poly(phenylene sulfide) and the like.


[0019] Among them, poly(phenylene ether) represented by the general formula [1] wherein X is -O- is preferable, and specific examples thereof include poly(1,4-phenylene ether), poly(2-methyl-1,4-phenylene ether), poly(2,6-dimethyl-1,4-phenylene ether), poly(2-phenyl-1,4-phenylene ether), poly(2,6-diphenyl-1,4-phenylene ether), poly(2-methyl-1,3-phenylene ether), poly(2,6-dimethyl-1,3-phenylene ether), poly(2-phenyl-1,3-phenylene ether), poly(2,6-diphenyl-1,3-phenylene ether) and the like, and among them, poly(1,4-phenylene ether), poly(2-phenyl-1,4-phenylene ether), poly(2,6-diphenyl-1,4-phenylene ether) are more preferable, and poly(2-phenyl-1,4-phenylene ether) is further preferable.

[0020] The precursor of a block having a repeating unit represented by the general formula [1] can be produced by a known method. For example, in the case of poly(phenylene ether), it can be produced by an oxidation polymerization method in which phenol is oxidized in the presence of a catalyst, or a method (called Ullmann reaction) in which a halogenated phenol is condensed in the presence of a catalyst and alkali.

[0021] Here, the term precursor of a block means a homopolymer having a reaction site which becomes a block by a copolymerization reaction.




In the formula [2], Ar<sup>1</sup> represents a group selected from the following structures,



in the above formulae,  $R^2$  represents an alkyl group having 1 to 6 carbon atoms, an alkoxy group having 1 to 6 carbon atoms, a phenyl group or a phenoxy group, b is an integer from 0 to 4, and c is an integer from 0 to 6. When a plurality of  $R^2$ s are present, these may be the same or different.

[0022] The precursor of a block having a repeating unit represented by the general formula [2] is obtained, for example, by ring-opening polymerization of a glycidyl ether having an aromatic ring, of the following formula:



[0023] Specific examples thereof include phenyl glycidyl ether, o-toluy glycidyl ether, m-toluy glycidyl ether, p-toluy glycidyl ether, 2,3-dimethylphenyl glycidyl ether, 2,4-dimethylphenyl glycidyl ether, 2,5-dimethylphenyl glycidyl ether, 2,6-dimethylphenyl glycidyl ether, 2,3,4-trimethylphenyl glycidyl ether, 2,4,6-trimethylphenyl glycidyl ether, 2,4,5, 6-tetramethylphenyl glycidyl ether, 2-ethylphenyl glycidyl ether, 4-ethylphenyl glycidyl ether, 2-propylphenyl glycidyl ether, 4-n-propylphenyl glycidyl ether, 4-propylphenyl glycidyl ether, 2-butylphenyl glycidyl ether, 4-butylphenyl glycidyl ether, 4-i-propylphenyl glycidyl ether, 2-biphenyl glycidyl ether, 4-biphenyl glycidyl ether, 1-naphthyl glycidyl ether, 2-naphthyl glycidyl ether and the like. These may be used alone, or a plurality of glycidyl ethers may be used to form a copolymer.

[0024] If necessary, precursors of blocks obtained by copolymerizing the above-mentioned glycidyl ether having an aromatic ring with an epoxy compound containing no aromatic ring can be used.


[0025] Examples of the epoxy compound containing no aromatic ring include ethylene oxide, propylene oxide, 1,2-epoxybutane, cyclohexane epoxide, epifluorohydrin, epichlorohydrin, epibromohydrin, trifluoropropylene oxide, methyl glycidyl ether, ethylglycidyl ether, propylglycidyl ether, butylglycidyl ether and the like.

[0026] When such a copolymer is used as one component of a block, the amount of a glycidyl ether component having an aromatic ring is preferably 60% by weight or more, more preferably 80% by weight or more since if the ratio of an epoxy component is higher, heat resistance of the whole polymer decreases.



[0027] Regarding the ring-opening polymerization of a glycidyl ether-compound containing an aromatic ring with an epoxy compound containing no aromatic ring, a lot of methods are known, and any of these known polymerization methods can be used. The number of repeating units represented by the general formula [2] is preferably from 2 to 200, more preferably from 5 to 50.

[0028] The term block composed of an epoxy resin means a block obtained from a precursor composed of a resin having one or more epoxy groups in the molecule (epoxy resin). It includes also a block having resultantly such a form even if an epoxy resin is not used as a precursor.

[0029] Among blocks composed of an epoxy resin, blocks composed of an epoxy resin having an aromatic ring in the main chain are preferable, and blocks having a repeating unit represented by the following general formula [3] are further preferable.



In the formula [3],  $Ar^2$  represents a group selected from the following structures,




in the above formulae,  $R^3$  represents an alkyl group having 1 to 6 carbon atoms, an alkoxy group having 1 to 6 carbon atoms or a phenyl group,  $d$  is an integer from 0 to 3, and  $e$  is an integer from 0 to 2. When a plurality of  $R^3$ s are present, these may be the same or different.  $Y$  represents  $-O-$ ,  $-S-$ , an alkylene group having 1 to 20 carbon atoms, a halogenated alkylene group having 1 to 10 carbon atoms or an alkylendioxy group having 1 to 20 carbon atoms. When a plurality of  $Y$ s are present, these may be the same or different.

**[0030]** The epoxy resin having a repeating unit represented by the general formula [3] can be usually synthesized by a known method of synthesizing an epoxy resin. As this method, there are listed a method in which a diol compound represented by  $HO-Ar-OH$  with epichlorohydrin in the presence of an alkali, and a method in which a diol compound and a diglycidyl ether compound are reacted.

**[0031]** Specific examples of the diol compound represented by  $HO-Ar-OH$  include hydroquinone, resorcinol, catechol, 1,2-dihydroxynaphthalene, 1,4-dihydroxynaphthalene, 1,5-dihydroxynaphthalene, 2,6-dihydroxynaphthalene, 2,7-dihydroxynaphthalene, 4,4'-dihydroxybiphenyl, 2,4'-dihydroxybiphenyl, 2,2'-dihydroxybiphenyl, 4,4'-dihydroxydiphenylmethane, 1,1-bis(4-hydroxyphenyl)ethane, 2,2-bis(4-hydroxyphenyl)propane, 2,2-bis(4-hydroxyphenyl)butane, 1,1-bis(4-hydroxyphenyl)cyclohexane, 2,2-bis(4-hydroxyphenyl)-1,1,1,3,3,3-hexafluoropropane, 1,1-bis(4-hydroxyphenyl)-1-phenylethane, bis(4-hydroxyphenyl)diphenylmethane, 9,9-bis(4-hydroxyphenyl)fluorene,  $\alpha,\alpha'$ -bis(4-hydroxyphenyl)-1,4-diisopropylbenzene, 4,4'-dihydroxydiphenyl ether, 2,2'-dihydroxydiphenyl ether, bis(4-hydroxyphenyl) sulfide, bis(2-hydroxyphenyl) sulfide, 1,2-bis(4-hydroxyphenyl)ethane, 1,2-bis(4-hydroxyphenoxy)ethane, 1,2-bis(3-hydroxyphenoxy)ethane, 1,2-bis(4-hydroxyphenoxy)propane, 1,3-bis(4-hydroxyphenoxy)propane, 1,4-bis(4-hydroxyphenoxy)butane, 1,6-bis(4-hydroxyphenoxy)hexane, diethylene glycol bis(4-hydroxyphenyl) ether and the like.

**[0032]** The number of repeating units constituting a block composed of an epoxy resin having a repeating unit represented by the general formula [3] is preferably from 2 to 200, more preferably from 4 to 50.

**[0033]** As the block containing substantially no sulfonic acid group, blocks composed of an aromatic polyether having a repeating unit represented by the general formula [4] are preferable because of high heat resistance.



**[0034]** In the general formula [4],  $R^4$  represents an alkyl group having 1 to 6 carbon atoms, and  $f$  is an integer from 0 to 4. When a plurality of  $R^4$ s are present, these may be the same or different.  $Z$  represents  $-CO-$  or  $-SO_2-$ .

**[0035]** Specifically, a block composed of polyether ketone, and a block composed of polyether sulfone are listed.

**[0036]** Among others, polyether sulfone of the general formula [4] wherein  $Z$  is  $-SO_2-$  is more preferable due to its higher solubility in a solvent.

**[0037]** Polyether sulfone, one example of a precursor of a block of the general formula [4], can be synthesized, for example, by polycondensing 4,4'-dihydroxydiphenylsulfone with 4,4'-dichlorodiphenylsulfone.

**[0038]** The weight-average molecular weight of a precursor of a block composed of polyether sulfone is preferably from 2000 to 500000, more preferably from 2000 to 100000. When the molecular weight is less than 2000, film strength

and heat resistance of a copolymer may lower, while when over 500000, solubility may decrease.

[0039] Next, a method for producing a polymer electrolyte of the present invention will be illustrated.

[0040] The method for producing a block copolymer by chemically bonding two or more precursors of blocks is not particularly restricted, and a suitable known method corresponding to a combination of blocks can be used.

[0041] For example, when poly(phenylene ether) as one example of a precursor of a block of the general formula [1] and polyether sulfone as one example of a precursor of a block of the general formula [4] are bonded, there is a method in which poly(phenylene ether) having a hydroxyl group remaining at the end and polyether sulfone having halogen remaining at the end are condensed in the presence of an alkali. Further, when poly(phenylene ether) having a hydroxyl group remaining at the end and polyether sulfone having a hydroxyl group remaining at the end are bonded, they can also be bonded according to the analogous condensation reaction using as a connecting agent a dihalogen compound such as 4,4'-difluorobenzophenone, 4,4'-dichlorodiphenylsulfone and the like.

[0042] On the other hand, when poly(phenyl glycidyl ether) as one example of a precursor of a block of the general formula [2] and polyether sulfone as one example of a precursor of a block of the general formula [4] are bonded, synthesis can be effected by converting the end hydroxyl group of polyether sulfone having a hydroxyl group at the end into alkali metal phenolate, conducting ring-opening polymerization of glycidyl ether containing an aromatic ring by using the phenolate as a polymerization initiation point, subsequently, conducting sulfonation.

[0043] Alternatively, there are exemplified a method in which a precursor of a block is first synthesized by copolymerizing phenyl glycidyl ether with glycidyl ether containing halogen which can be used in a block forming reaction such as epichlorohydrin and the like, then, the precursor is condensed with polyether sulfone having a hydroxyl group remaining at the end in the presence of an alkali, and other methods.

[0044] Further, when an epoxy resin as one example of a precursor of a block of the general formula [3] and polyether sulfone as one example of a precursor of a block of the general formula [4] are bonded, there is a method in which a glycidyl group remaining at the end of the epoxy resin is bonded to a hydroxyl group remaining at the end of the polyether sulfone by ring-opening addition.

[0045] When polyether sulfone is used as one precursor of a block, a block copolymerization reaction is preferably conducted in a suitable solvent though it can be effected in molten condition using no solvent. As the solvent, aromatic hydrocarbon-based solvent, ether-based solvents, ketone-based solvent, amide-based solvent, sulfone-based solvent, sulfoxide-based solvent and the like can be used, and amide-based solvents are preferable because of high solubility. Here, as the amide-based solvent, N,N-dimethylformamide, N,N-dimethylacetamide, N-methylpyrrolidone and the like are listed.

[0046] The reaction temperature of the block copolymerization reaction is preferably from 20 to 250°C, more preferably from 50 to 200°C.

[0047] In a block copolymer used in the present invention, the amount of a block having substantially no sulfonic acid group is preferably from 60 to 95% by weight, further preferably from 70 to 90% by weight based on the total amount of the block copolymer. When the amount of a block having substantially no sulfonic acid group is over 95% by weight, sufficient performance as a polymer electrolyte may not be obtained since ion exchange capacity in a block copolymer is low after introduction of sulfonic acid groups, while, when less than 60% by weight, water resistance of a block copolymer after introduction of sulfonic acid groups may decrease.

[0048] In a block copolymer used in the present invention, a method for introducing sulfonic acid groups into a specific block is not particularly restricted, and there are listed: (a) a method in which a precursor of a block having previously introduced sulfonic acid groups and a precursor of a block having substantially no sulfonic acid group are copolymerized; (b) a method in which a copolymer composed of a block to which a sulfonic acid group is to be introduced and a block to which a sulfonic acid group is to be substantially not introduced is produced, and then sulfonic acid groups are selectively introduced into the block to which a sulfonic acid group is to be introduced in the above-mentioned copolymer; and other methods. The above-mentioned method (b) is preferable since the precursor of a block having previously introduced sulfonic acid groups may block a copolymerization reaction.

[0049] In the above-mentioned method (a), a precursor of a block having sulfonic acid groups can be produced, for example, by sulfonating the precursor of a block. As a sulfonating agent, known sulfonating agents such as sulfuric acid having a concentration of 90% or more, fuming sulfuric acid, chlorosulfonic acid, SO<sub>3</sub> and the like can be used.

[0050] In the above-mentioned method (b), as the method for selectively introducing sulfonic acid groups into a copolymer, there is (c) a method in which functional groups present in a block to which a sulfonic acid group is to be introduced but not present in a block to which a sulfonic acid group is to be substantially not introduced is utilized. Alternatively, there is envisaged (d) a method utilizing difference in reactivity on a sulfonation reaction of a block to which a sulfonic acid group is to be introduced with a block to which a sulfonic acid group is to be substantially not introduced.

[0051] As an example of the above-mentioned method (d), there is a method for producing a polymer electrolyte comprising the steps of reacting a precursor of a block having a repeating unit represented by the general formula [1], [2] or [3] with a precursor of a block having a repeating unit represented by the general formula [4] to produce a block

copolymer, and subsequently, sulfonating the copolymer.

[0052] For example, in a sulfonation reaction of an aromatic ring using sulfuric acid as a sulfonating agent, it is known that the reactivity of an aromatic ring of a block having a repeating unit represented by the general formula [4] is lower in comparison with that of an aromatic ring of a block having a repeating unit represented by the general formula [1], [2] or [3].

[0053] Therefore, by sulfonating with sulfuric acid, under suitable conditions, a block copolymer obtained by reacting a precursor of a block having a repeating unit represented by the general formula [4] and a precursor of a block having a repeating unit represented by the general formula [1], [2] or [3], there can be produced a block copolymer in which sulfonic acid groups are selectively introduced into a block having a repeating unit represented by the general formula [1], [2] or [3] but a sulfonic acid group is not substantially introduced into a block represented by the general formula [4].

[0054] In a process of sulfonation (introduction of a sulfonic acid group), known sulfonating agents such as sulfuric acid having a concentration of 90% or more, fuming sulfuric acid, chlorosulfonic acid,  $\text{SO}_3$  and the like can be used. Among them, sulfuric acid having a concentration of 90% or more is preferable, and sulfuric acid having a concentration of 94 to 99% by weight is more preferable.

[0055] Further, organic solvents which are not concerned with a sulfonation reaction may also be added in small amount together with sulfuric acid, so that a sulfonation reaction of a block copolymer progresses in a uniform system. The amount of these organic solvents is not included in % by weight of sulfuric acid concentration described above.

[0056] Dissolution into sulfuric acid and sulfonation of a block copolymer progress simultaneously, and at room temperature, the reaction is usually completed in 2 to 20 hours to give a uniform solution. The sulfonated block copolymer can be recovered by pouring a sulfuric acid solution into a large amount of water.

[0057] The concentration of a block copolymer against sulfuric acid is preferably from 1 to 50% by weight, more preferably from 5 to 30% by weight. The reaction temperature is preferably from 0 to 80°C, more preferably from 20 to 40°C.

[0058] Further, in producing an electrolyte of the present invention, there can be used additives such as plasticizers, stabilizers, releasing agents and the like used in usual polymers, in amount in a range wherein the object of the present invention does not deteriorate.

[0059] Moreover, in producing an electrolyte of the present invention or in processing such as film forming and the like, and molding an electrolyte of the present invention, an intermolecular crosslinking structure can be introduced, in amount in a range wherein the object of the present invention does not deteriorate.

[0060] Precursors of a block having a repeating unit represented by the general formulae [1] to [4] is synthesized by a previously secured technology, and is a cheap material used in large scale. Also copolymers obtained by synthesis using them as a raw material and by sulfonation thereof are extremely inexpensive as compared with fluorine-based materials such as Nafion and the like.

[0061] When a polymer electrolyte of the present invention is used in a fuel cell, it is usually used in the form of film (hereinafter, sometimes referred to as fuel cell polymer electrolyte film). A method for converting a polymer electrolyte of the present invention into a film is not particularly restricted, and a method of forming a film from solution condition (solution cast method) is preferable.

[0062] Specifically, a film is formed by dissolving a polymer electrolyte in a suitable solvent, casting the solution on a glass substrate, and removing the solvent. The solvent used in film formation is not particularly restricted provided it can dissolve a polymer electrolyte and can be removed thereafter, and there can be suitably used aprotic polar solvents such as N,N-dimethylformamide, N,N-dimethylacetamide, N-methyl-2-pyrrolidone, dimethylsulfoxide and the like, chlorine-based solvents such as dichloromethane, chloroform, 1,2-dichloroethane, chlorobenzene, dichlorobenzene and the like, alcohols such as methanol, ethanol, propanol and the like, and alkylene glycol monoalkyl ethers such as ethylene glycol monomethyl ether, ethylene glycol monoethyl ether, propylene glycol monomethyl ether, propylene glycol monoethyl ether and the like. These may be used alone, and if necessary, two or more solvents may also be mixed and used. Among them, dimethylformamide, dimethylacetamide, N-methylpyrrolidone and dimethylsulfoxide are preferable due to high solubility of the polymer.

[0063] The thickness of a film is not particularly restricted, and preferably from 10 to 200  $\mu\text{m}$ . For obtaining film strength which can stand practical use, a thickness of 10  $\mu\text{m}$  or more is preferable, and for lowering film resistance, namely, for improving power generation ability, a thickness of 200  $\mu\text{m}$  or less is preferable. The film thickness can be controlled depending on solution concentration or applied thickness on a substrate.

[0064] Next, a fuel cell of the present invention will be illustrated.

[0065] A fuel cell of the present invention can be produced by bonding a catalyst and a conductive substance as a collector on both surfaces of a fuel cell polymer electrolyte film.

[0066] The catalyst is not particularly restricted providing it can activate an oxidation and reduction reaction with hydrogen or oxygen, and known catalysts can be used and preferable is use of a fine particle of platinum. A fine particle of platinum is often supported on particulate or fibrous carbon such as activated carbon, graphite and the like before being used preferably.

[0067] Regarding the conductive substance as a collector, known materials can be used, and porous carbon non-woven fabric or carbon paper are preferable since they transport a raw material gas to a catalyst efficiently.

[0068] Regarding a method for bonding a platinum fine particle or carbon carrying thereon a platinum fine particle to porous carbon non-woven fabric or carbon paper, and a method for bonding it to a polymer electrolyte film, there can be used, for example, known methods described in J. Electrochem. Soc. : Electrochemical Science and Technology, 1988, 135 (9), 2209, and the like.

#### EXAMPLES

[0069] The following examples illustrate the present invention below, but do not limit the scope of the present invention at all.

#### Comparative Example 1

[0070] 4,4'-dihydroxydiphenylsulfone; 4,4'-dihydroxybiphenyl and 4,4'-dichlorodiphenylsulfone were polycondensed at a molar ratio of 7:3:10 at a temperature from 200 to 290°C using diphenylsulfone as a solvent in the co-existence of potassium carbonate. The resulted polymer was sulfonated with conc. sulfuric acid to synthesize a random copolymer in which a sulfonic acid group had been introduced into a biphenyl unit.

#### Reference Example 1

[0071] 99 mg of anhydrous cuprous chloride and 266 mg of 2-methylbenzimidazole were stirred for 15 minutes under atmospheric pressure at room temperature in 1 ml of toluene. To this was added 8.5 g of 2-phenylphenol and 30 ml of toluene, and the mixture was stirred for 5 hours at 50°C under oxygen atmosphere. After completion of the reaction, methanol containing hydrochloric acid was poured into this to precipitate a polymer, and this was filtrated and dried to obtain poly(2-phenylphenylene ether)(hereinafter, referred to as PE1).

[0072] 12.25 g of 2-phenylphenol and 1.49 g of 4,4'-dihydroxybiphenyl were oxidation-polymerized using the same catalyst and using chlorobenzene as a solvent, to obtain poly(2-phenylphenylene ether) having a hydroxyl group on both ends (hereinafter, referred to as PE2).

#### Reference Example 2

[0073] 99 mg of anhydrous cuprous chloride and 65 mg of N,N,N',N'-tetramethyl-1,3-propanediamine were stirred for 15 minutes under atmospheric pressure at room temperature in 5 ml of chlorobenzene. To this was added 4.43 g of 2,6-diphenylphenol, 0.37 g of 4,4'-dihydroxybiphenyl and 15 ml of chlorobenzene, and the mixture was stirred for 5 hours at 60°C under oxygen atmosphere. After completion of the reaction, methanol containing hydrochloric acid was poured into this to precipitate a polymer, and this was filtrated and dried to obtain poly(2,6-diphenylphenylene ether) having hydroxyl groups on both ends (hereinafter, referred to as PE3).

#### Example 1

[0074] Into a flask equipped with an azeotropic distillation apparatus was charged 3.0 g of Sumika Excel PES5003P (manufactured by Sumitomo Chemical Co., Ltd., hydroxyl group-ended polyether sulfone), 0.75 g of PE1, 0.04 g of potassium carbonate, 15 ml of N,N-dimethylacetamide (hereinafter, referred to as DMAc) and 3 ml of toluene, the mixture was heated while stirring, and the solution was dehydrated under azeotropic condition of toluene and water, then, toluene was distilled off. To this was added 0.05 g of 4,4'-difluorobenzophenone, and the mixture was stirred while heating at 160°C for 5 hours. The reaction solution was added dropwise to a large amount of acidic methanol containing hydrochloric acid, the resulted precipitate was recovered by filtration, and dried under reduced pressure at 80°C to obtain 3.8 g of a block copolymer.

[0075] 2 g of the resulted block copolymer was stirred together with 20 ml of 98% sulfuric acid at room temperature to obtain a uniform solution, then, further stirred for 2 hours. The resulted solution was added into a large amount of ice water dropwise, and the resulted precipitate was recovered by filtration. Further, mixer washing with ion exchange water was repeated until the washing solution became neutral, then, the polymer was dried at 40°C under reduced pressure to obtain a sulfonated block copolymer.

#### Example 2

[0076] Into a flask equipped with an azeotropic distillation apparatus was charged 50 g of Sumika Excel PES5003P,



0.36 g of potassium carbonate, 180 ml of DMAc and 25 ml of toluene. The system was purged with nitrogen, and the mixture was heated while stirring for 2 hours under azeotropic condition of toluene and water, then, toluene was distilled off. To this was added 9.5 g of 4,4'-difluorobenzophenone, and the mixture was stirred while heating at 160°C for 5 hours. The reaction solution was added dropwise to a large amount of methanol, and the produced precipitate was recovered by filtration. The resulted precipitate was washed while stirring for 5 hours with a large amount of acetone with heating under reflux, then, removed out from acetone, and dried under reduced pressure at 80°C to obtain 45 g of chain end fluorinated polyether sulfone.

[0077] Into a flask equipped with an azeotropic distillation apparatus was charged 0.75 g of PE2, 0.03 g of potassium carbonate, 15 ml of DMAc and 3 ml of toluene. The solution was dehydrated under azeotropic condition of toluene and water, then, toluene was distilled off. To this was added 3 g of the chain end fluorinated polyether sulfone, and the mixture was stirred while heating at 160°C for 5 hours. The reaction solution was added dropwise to a large amount of acidic methanol containing hydrochloric acid, and the resulted precipitate was recovered by filtration, and dried under reduced pressure at 40°C to obtain 3.6 g of a block copolymer.

[0078] The resulted block copolymer was sulfonated using 98% sulfuric acid in the same manner as in Example 1, to obtain a sulfonated block copolymer.

#### Example 3

[0079] 9.8 g of a block copolymer was obtained by reacting 8.0 g of Sumika Excel PES5003P, 2.0 g of PE3, 0.2 g of potassium carbonate, 0.26 g of 4,4'-difluorobenzophenone, 50 ml of DMAc and 5 ml of toluene in the same manner as in Example 1. The resulted block copolymer was sulfonated using 98% sulfuric acid, to obtain a sulfonated block copolymer.

#### Reference Example 3

[0080] 0.2 g of anhydrous Fe(III) chloride and 1 ml of propylene oxide were stirred for 10 minutes at 0°C in 4 ml of ether, then, ether and volatile components were removed by raising the temperature to room temperature and under reduced pressure, to prepare a catalyst. To this was added 28.53 g of phenyl glycidyl ether and 0.925 g of epichlorohydrin, and the mixture was stirred while heating at 100°C for 1 hour and at 160°C for 8 hours. The polymerization solution was poured into methanol to obtain a precipitate which was filtrated and dried to obtain a polymer of poly(phenyl glycidyl ether-co-epichlorohydrin) (hereinafter, referred to as GE1).

[0081] In the same manner, 17.74 g of phenyl glycidyl ether and 2.37 g of epichlorohydrin were used to synthesize a polymer of poly(phenyl glycidyl ether-co-epichlorohydrin) (hereinafter, referred to as GE2).

#### Example 4

[0082] 8.0 g of PES5003P and 0.1 g of potassium carbonate were dissolved in 40 ml of DMAc and 5 ml of toluene, and the mixture was heated to distill toluene. To this was added 2.0 g of GE1, and the mixture was stirred while heating at 160°C for 3.5 hours. The reaction solution was poured into dilute hydrochloric acid to precipitate a polymer which was filtrated, washed with water and dried to recover a block copolymer.

[0083] 6.0 g of the resulted block copolymer and 40 g of conc. sulfuric acid were mixed and dissolved, then, the solution was poured into a large amount of water to precipitate a polymer which was filtrated, washed with water and dried to obtain a sulfonated block copolymer.

#### Example 5

[0084] A block copolymerization reaction and sulfonation reaction were conducted in the same manner as in Example 4 except that 3.0 g of GE1 was used, to obtain a sulfonated block copolymer.

#### Example 6

[0085] A block copolymerization reaction and sulfonation reaction were conducted in the same manner as in Example 4 except that 2.0 g of GE2 was used instead of GE1, to obtain a sulfonated block copolymer.

#### Reference Example 4

[0086] 19.8 g of hydroquinone, 18.5 g of epichlorohydrin and 8.8 g of sodium hydroxide were heated while stirring in 100 ml of water to synthesize an epoxy polymer having a glycidyl group on both ends (hereinafter, referred to as EP1).

[0087] In the same manner, 49.3 g of 1,2-bis(3-hydroxyphenoxy)ethane, 22.2 g of epichlorohydrin and 12.0 g of sodium hydroxide were used to synthesize an epoxy polymer (hereinafter, referred to as EP2).

#### Example 7

[0088] 20.0 g of PES5003P was dissolved in 100 ml of DMAc, to this was added 3.87 g of EP1, 0.321 g of 4,4'-dihydroxybenzophenone and 0.2 ml of quinoline, and the mixture was stirred while heating at 150°C for 4 hours. The reaction solution was poured into dilute hydrochloric acid to precipitate a polymer which was filtrated, washed with water and dried to recover a block copolymer.

[0089] 20.0 g of the resulted block copolymer was mixed with and dissolved into 80 g of conc. sulfuric acid, then, poured into a large amount of water to precipitate a polymer which was filtrated, washed with water and dried to obtain a sulfonated block copolymer.

#### Example 8

[0090] A copolymerization reaction and sulfonation reaction were conducted in the same manner as in Example 7 using 40.0 g of PES5003P, 7.05 g of EP2, 0.686 g of 4,4'-dihydroxybenzophenone and 0.5 ml of quinoline. Cast film formation from a DMAc solution was conducted to obtain a film which had a tensile strength of 450 kg/cm<sup>2</sup> and a temperature at 10% heating loss of 265°C.

#### Example 9

[0091] A copolymerization reaction and sulfonation reaction were conducted in the same manner as in Example 7 using 8.0 g of PES5003P, 1.50 g of EP2, 0.14 g of 4,4'-dihydroxybiphenyl and 0.2 ml of quinoline, to recover a sulfonated block copolymer.

#### Example 10

[0092] A copolymerization reaction and sulfonation reaction were conducted in the same manner as in Example 7 using 8.0 g of PES5003P, 2.25 g of EP2, 0.223 g of 4,4'-dihydroxybiphenyl and 0.2 ml of quinoline, to recover a sulfonated copolymer.

[0093] The sulfonated block copolymers obtained in Examples 1 to 10 and the sulfonated random copolymer obtained in Comparative Examples 1 were dissolved each in a concentration of 5 to 20% by weight into DMAc, and cast on glass substrates to form films which were dried to obtain films. The proton conductivity of the film was measured according to an alternating method under conditions of a temperature of 80°C and a humidity of 95%. Further, the dried film was immersed in de-ionized water at 100°C for 2 hours, then, increase in the film weight was measured based on the weight in dry condition, to give water absorption of the film. The results are summarized in Table 1. Table 1

	Proton conductivity (S/cm)	Water absorption (%)
Comparative example 1	$1.3 \times 10^{-2}$	24
Example 1	$1.0 \times 10^{-1}$	79
Example 2	$8.4 \times 10^{-2}$	63
Example 3	$5.1 \times 10^{-2}$	38
Example 4	$5.7 \times 10^{-2}$	43
Example 5	$1.4 \times 10^{-1}$	55
Example 6	$6.3 \times 10^{-2}$	41
Example 7	$7.3 \times 10^{-2}$	7
Example 8	$1.1 \times 10^{-1}$	35
Example 9	$1.3 \times 10^{-1}$	32
Example 10	$2.8 \times 10^{-1}$	86


[0094] From the above-mentioned results, it is known that a polymer electrolyte containing a block copolymer of the

present invention has the equivalent or more proton conductivity, water absorption suppressed relatively low, and excellent water resistance, as compared with a polymer electrolyte into which a sulfonic acid group has been randomly introduced.

[0095] A polymer electrolyte of the present invention can be produced at lower cost, and can reduce production cost of a fuel cell using this electrolyte. Further, it is suitable for a proton conductive film of a fuel cell due to excellent water resistance and heat resistance, and high proton conductivity.


# Claims

1. A polymer electrolyte containing a block copolymer comprising one or more blocks having sulfonic acid groups and one or more blocks having substantially no sulfonic acid group, and at least one block among all the blocks is a block having aromatic rings in the main chain thereof.
2. The polymer electrolyte according to Claim 1, wherein the blocks having sulfonic acid groups have a structure where the sulfonic acid groups are directly bonded to the aromatic rings.
3. The polymer electrolyte according to Claim 1 or 2, wherein the blocks having sulfonic acid groups are blocks composed of the repeating units represented by the general formula [1] into which sulfonic acid groups have been introduced:




in the formula, X represents -O-, -S-, -NH- or direct bond, R<sup>1</sup> represents an alkyl group having 1 to 6 carbon atoms, an alkoxy group having 1 to 6 carbon atoms or a phenyl group, and a is an integer from 0 to 3, and when a plurality of R<sup>1</sup>s are present, these may be the same or different.

4. The polymer electrolyte according to Claim 3, wherein X is -O- in the general formula [1].
5. The polymer electrolyte according to Claim 1 or 2, wherein the blocks having sulfonic acid groups are blocks composed of the repeating units represented by the general formula [2] into which sulfonic acid groups have been introduced:




in the formula, Ar<sup>1</sup> represents a group selected from the following structures,




in the formulae,  $R^2$  represents an alkyl group having 1 to 6 carbon atoms, an alkoxy group having 1 to 6 carbon atoms, a phenyl group or a phenoxy group, b is an integer from 0 to 4, and c is an integer from 0 to 6, and when a plurality of  $R^2$ s are present, these may be the same or different.

6. The polymer electrolyte according to Claim 1 or 2, wherein the blocks having sulfonic acid groups are blocks composed of an epoxy resin into which sulfonic acid groups have been introduced.
7. The polymer electrolyte according to Claim 6, wherein the blocks having sulfonic acid groups are blocks having a repeating unit represented by the general formula [3] into which sulfonic acid groups have been introduced:




in the formula [3],  $\text{Ar}^2$  represents a group selected from the following structures,



in the formulae,  $R^3$  represents an alkyl group having 1 to 6 carbon atoms, an alkoxy group having 1 to 6 carbon atoms or a phenyl group, d is an integer from 0 to 3, and e is an integer from 0 to 2; when a plurality of  $R^3$ s are present, these may be the same or different; Y represents -O-, -S-, an alkylene group having 1 to 20 carbon atoms, a halogenated alkylene group having 1 to 10 carbon atoms or an alkylenedioxy group having 1 to 20 carbon atoms; and when a plurality of Ys are present, these may be the same or different.

8. The polymer electrolyte according to Claim 1 or 2, wherein the blocks having substantially no sulfonic acid group are aromatic polyethers having a repeating unit represented by the general formula [4]:



in the formula,  $R^4$  represents an alkyl group having 1 to 6 carbon atoms; f is an integer from 0 to 4; when a plurality of  $R^4$ s are present, these may be the same or different; and Z represents -CO- or -SO<sub>2</sub>-.

9. The polymer electrolyte according to Claim 8, wherein Z is -SO<sub>2</sub>- in the general formula [4].
10. The polymer electrolyte according to Claim 1 or 2, wherein the amount of the block having substantially no sulfonic acid group is from 60 to 95% by weight based on the weight of the whole block copolymer.

11. A method for producing a polymer electrolyte of Claims 1 to 10, comprising the steps of: reacting a precursor of a block having repeating units represented by the general formula [1], [2] or [3], with a precursor of a block having a repeating unit represented by the general formula [4] to produce a block copolymer; and then sulfonating said copolymer.

5

12. The method for producing a polymer electrolyte according to Claim 11, wherein it comprises a step of sulfonating the block copolymer with sulfuric acid having a concentration of 90% or more.

13. A fuel cell obtainable by using a polymer electrolyte of any one of Claims 1 to 10.

10

15

20

25

30

35

40

45

50

55

(19)



Europäisches Patentamt  
European Patent Office  
Office européen des brevets



(11)

**EP 1 113 517 A3**

(12)

**EUROPEAN PATENT APPLICATION**

(88) Date of publication A3:  
30.07.2003 Bulletin 2003/31

(51) Int Cl.7: **H01M 8/10**, H01B 1/12,  
C08F 8/36

(43) Date of publication A2:  
04.07.2001 Bulletin 2001/27

(21) Application number: **00128267.2**

(22) Date of filing: **22.12.2000**

(84) Designated Contracting States:  
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU  
MC NL PT SE TR**  
Designated Extension States:  
**AL LT LV MK RO SI**

(30) Priority: **27.12.1999 JP 37068999**  
**07.03.2000 JP 2000061768**

(71) Applicant: **Sumitomo Chemical Company,  
Limited**  
**Chuo-ku Osaka 541-8550 (JP)**

(72) Inventors:  
• **Terahara, Atsushi**  
**Tsukuba-shi, Ibaraki (JP)**  
• **Iwasaki, Katsuhiko**  
**Tsukuba-shi, Ibaraki (JP)**  
• **Ikeda, Takashi**  
**Tsukuba-shi, Ibaraki (JP)**

(74) Representative: **Henkel, Feiler, Hänzel**  
**Möhlstrasse 37**  
**81675 München (DE)**

(54) **Polymer electrolyte and method for producing the same**

(57) Provided is a polymer electrolyte containing a block copolymer comprising one or more blocks having sulfonic acid groups and one or more blocks having substantially no sulfonic acid group, and at least one block among all blocks is a block having aromatic rings in the main chain thereof, and a method for producing the

same. The polymer electrolyte is suitable for a proton conductive film of a fuel cell due to excellent water resistance and heat resistance, and high proton conductivity.

**EP 1 113 517 A3**



European Patent  
Office

## EUROPEAN SEARCH REPORT

Application Number  
EP 00 12 8267

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
X	US 5 438 082 A (RITTER HELMUT ET AL) 1 August 1995 (1995-08-01) * the whole document *	1-4, 10-13	H01M8/10 H01B1/12 C08F8/36
X	US 5 561 202 A (RITTER HELMUT ET AL) 1 October 1996 (1996-10-01) * the whole document *	1-4, 10-13	
X	US 5 741 408 A (RITTER HELMUT ET AL) 21 April 1998 (1998-04-21) * the whole document *	1-4, 10-13	
X	US 5 834 566 A (HELMER-METZMANN FREDDY ET AL) 10 November 1998 (1998-11-10) * the whole document *	1-4, 10-13	
A	PATENT ABSTRACTS OF JAPAN vol. 1998, no. 06. 30 April 1998 (1998-04-30) -& JP 10 045913 A (SUMITOMO CHEM CO LTD), 17 February 1998 (1998-02-17) * the whole document *	1-4, 10-13	
A	US 5 429 759 A (ANDRIEU XAVIER ET AL) 4 July 1995 (1995-07-04) *column 2, lines 5-9 and lines 65-68; column 3, line 30; claims 1,3,4*	5-7, 11-13	H01M H01B C08L C08G C08F
A	US 3 751 376 A (QUENTIN J) 7 August 1973 (1973-08-07) *column 1, lines 20-25 and line 57; column 3, lines 15-35*	6,7, 11-13	
X	WO 96 29360 A (CLAUSS JOACHIM ;DECKERS GREGOR (DE); HOECHST AG (DE); WITTELER HEL) 26 September 1996 (1996-09-26) *pages 1, 3, 4, 5, 8, 15-19; claims 1, 5*	8,9, 11-13	
		-/--	
The present search report has been drawn up for all claims			
Place of search MUNICH		Date of completion of the search 2 June 2003	Examiner Boussard, N
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document	

EPO FORM 1503 03/02 (P04C01)



European Patent  
Office

# EUROPEAN SEARCH REPORT

Application Number  
EP 00 12 8267

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
X	EP 0 575 807 A (HOECHST AG) 29 December 1993 (1993-12-29) *page 2, lines 50-55; page 3, lines 50-52; page 4, lines 10-35* ---	8,9, 11-13	
X	EP 0 932 213 A (SUMITOMO CHEMICAL CO) 28 July 1999 (1999-07-28) *page 3, lines 1-52; page 4, lines 1-50* ---	8,9, 11-13	
A	EP 0 008 894 A (ICI PLC) 19 March 1980 (1980-03-19) * the whole document * -----	8,9, 11-13	
The present search report has been drawn up for all claims			TECHNICAL FIELDS SEARCHED (Int.Cl.7)
Place of search <b>MUNICH</b>		Date of completion of the search <b>2 June 2003</b>	Examiner <b>Boussard, N</b>
<p><b>CATEGORY OF CITED DOCUMENTS</b></p> <p>X : particularly relevant if taken alone  Y : particularly relevant if combined with another document of the same category  A : technological background  O : non-written disclosure  P : intermediate document</p> <p>T : theory or principle underlying the invention  E : earlier patent document, but published on, or after the filing date  O : document cited in the application  L : document cited for other reasons  &amp; : member of the same patent family, corresponding document</p>			

EPO FORM 1503 03 82 (P04C01)





European Patent  
Office

Application Number

EP 00 12 8267

### CLAIMS INCURRING FEES

The present European patent application comprised at the time of filing more than ten claims.

- ☐ Only part of the claims have been paid within the prescribed time limit. The present European search report has been drawn up for the first ten claims and for those claims for which claims fees have been paid, namely claim(s):
- ☐ No claims fees have been paid within the prescribed time limit. The present European search report has been drawn up for the first ten claims.

### LACK OF UNITY OF INVENTION

The Search Division considers that the present European patent application does not comply with the requirements of unity of invention and relates to several inventions or groups of inventions, namely:

see sheet B

- ☒ All further search fees have been paid within the fixed time limit. The present European search report has been drawn up for all claims.
- ☐ As all searchable claims could be searched without effort justifying an additional fee, the Search Division did not invite payment of any additional fee.
- ☐ Only part of the further search fees have been paid within the fixed time limit. The present European search report has been drawn up for those parts of the European patent application which relate to the inventions in respect of which search fees have been paid, namely claims:
- ☐ None of the further search fees have been paid within the fixed time limit. The present European search report has been drawn up for those parts of the European patent application which relate to the invention first mentioned in the claims, namely claims:



European Patent  
Office

LACK OF UNITY OF INVENTION  
SHEET B

Application Number  
EP 00 12 8267

The Search Division considers that the present European patent application does not comply with the requirements of unity of invention and relates to several inventions or groups of inventions, namely:

1. Claims: 1-4,  
10-13 (insofar as they concern the blocks  
composed of the units represented by the general  
formula '1!)

Product claims 1-4 and 10 disclose a polymer electrolyte containing a block copolymer comprising one or more blocks having sulphonic acid groups (units represented by the general formula 1) and one or more blocks having substantially no sulphonic acid groups, wherein at least one block among all the blocks is a block having aromatic rings in the main chain.

Method claims 11 and 12 disclose a method of producing said polymer electrolyte and product claim 13 discloses a fuel cell using said polymer electrolyte.

2. Claims: 5,  
11-13 (insofar as they concern the blocks composed  
of the units represented by the general formula  
'2!)

Product claim 5 discloses a polymer electrolyte containing a block copolymer comprising one or more blocks having sulphonic acid groups (units represented by the general formula 2) and one or more blocks having substantially no sulphonic acid groups, wherein at least one block among all the blocks is a block having aromatic rings in the main chain.

Method claims 11 and 12 disclose a method of producing said polymer electrolyte and product claim 13 discloses a fuel cell using said polymer electrolyte.

3. Claims: 6,7,  
11-13 (insofar as they concern the blocks  
composed of an epoxy resin)

Product claims 6 and 7 disclose a polymer electrolyte containing a block copolymer comprising one or more blocks having sulphonic acid groups (epoxy resin) and one or more blocks having substantially no sulphonic acid groups, wherein at least one block among all the blocks is a block having aromatic rings in the main chain.

Method claims 11 and 12 disclose a method of producing said polymer electrolyte and product claim 13 discloses a fuel cell using said polymer electrolyte.



European Patent  
Office

LACK OF UNITY OF INVENTION  
SHEET B

Application Number

EP 00 12 8267

The Search Division considers that the present European patent application does not comply with the requirements of unity of invention and relates to several inventions or groups of inventions, namely:

4. Claims: 8,9,  
11-13 (insofar as they concern the blocks composed  
of the units represented by the general formula  
'4!)

Product claims 8 and 9 disclose a polymer electrolyte containing a block copolymer comprising one or more blocks having sulphonic acid groups and one or more blocks having substantially no sulphonic acid groups (units represented by the general formula 4), wherein at least one block among all the blocks is a block having aromatic rings in the main chain.

Method claims 11 and 12 disclose a method of producing said polymer electrolyte and product claim 13 discloses a fuel cell using said polymer electrolyte.

**ANNEX TO THE EUROPEAN SEARCH REPORT  
ON EUROPEAN PATENT APPLICATION NO.**

EP 00 12 8267

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on  
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

02-06-2003

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5438082 A	01-08-1995	CA 2098238 A1	14-12-1993
		DE 59309908 D1	27-01-2000
		EP 0574791 A2	22-12-1993
		JP 3342106 B2	05-11-2002
		JP 6093114 A	05-04-1994
		JP 2002220458 A	09-08-2002
		JP 2003086023 A	20-03-2003
		SG 73410 A1	20-06-2000
		US 5741408 A	21-04-1998
		US 5561202 A	01-10-1996
US 5561202 A	01-10-1996	US 6214488 B1	10-04-2001
		CA 2098238 A1	14-12-1993
		DE 59309908 D1	27-01-2000
		EP 0574791 A2	22-12-1993
		JP 3342106 B2	05-11-2002
		JP 6093114 A	05-04-1994
		JP 2002220458 A	09-08-2002
		JP 2003086023 A	20-03-2003
		SG 73410 A1	20-06-2000
		US 5438082 A	01-08-1995
US 5741408 A	21-04-1998	US 5741408 A	21-04-1998
		US 6214488 B1	10-04-2001
		CA 2098238 A1	14-12-1993
		DE 59309908 D1	27-01-2000
		EP 0574791 A2	22-12-1993
		JP 3342106 B2	05-11-2002
		JP 6093114 A	05-04-1994
		JP 2002220458 A	09-08-2002
		JP 2003086023 A	20-03-2003
		SG 73410 A1	20-06-2000
US 5834566 A	10-11-1998	US 5438082 A	01-08-1995
		US 5561202 A	01-10-1996
		DE 4422158 A1	04-01-1996
JP 10045913 A	17-02-1998	EP 0688824 A2	27-12-1995
		JP 8020716 A	23-01-1996
US 5429759 A	04-07-1995	US 6087031 A	11-07-2000
US 5429759 A	04-07-1995	FR 2695131 A1	04-03-1994
		AT 156937 T	15-08-1997
		CA 2105231 A1	02-03-1994
		DE 69313063 D1	18-09-1997

EPO FORM P4459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

**ANNEX TO THE EUROPEAN SEARCH REPORT  
ON EUROPEAN PATENT APPLICATION NO.**

EP 00 12 8267

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on  
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

02-06-2003

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5429759 A		DE 69313063 T2	11-12-1997
		EP 0591014 A1	06-04-1994
		ES 2105164 T3	16-10-1997
		JP 6196016 A	15-07-1994
US 3751376 A	07-08-1973	FR 2097260 A5	03-03-1972
		BE 768672 A1	17-12-1971
		CH 526603 A	15-08-1972
		DE 2130338 A1	23-12-1971
		ES 392413 A1	16-08-1973
		GB 1295798 A	08-11-1972
		IL 37084 A	29-11-1974
		JP 54014160 B	05-06-1979
		LU 63362 A1	21-03-1972
		NL 7107974 A	21-12-1971
		SU 378019 A3	17-04-1973
		ZA 7103956 A	23-02-1972
WO 9629360 A	26-09-1996	DE 19510026 A1	26-09-1996
		DE 19545642 A1	12-06-1997
		DE 19548423 A1	26-06-1997
		DE 19610303 A1	25-09-1997
		CA 2215911 A1	26-09-1996
		WO 9629360 A1	26-09-1996
		EP 0815160 A1	07-01-1998
EP 0575807 A	29-12-1993	JP 11502249 T	23-02-1999
		CA 2098159 A1	12-12-1993
		DE 59310005 D1	18-05-2000
		EP 0575807 A1	29-12-1993
		JP 6049202 A	22-02-1994
		SG 46643 A1	20-02-1998
EP 0932213 A	28-07-1999	US 5362836 A	08-11-1994
		JP 10021943 A	23-01-1998
		US 5985477 A	16-11-1999
		EP 0932213 A1	28-07-1999
EP 0008894 A	19-03-1980	DE 2964541 D1	24-02-1983
		DE 2964904 D1	31-03-1983
		DE 2966289 D1	10-11-1983
		EP 0008894 A1	19-03-1980
		EP 0008895 A1	19-03-1980
		EP 0029633 A2	03-06-1981
		JP 3021333 A	30-01-1991
		JP 1512209 C	09-08-1989

EPO FORM P0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

**ANNEX TO THE EUROPEAN SEARCH REPORT  
ON EUROPEAN PATENT APPLICATION NO.**

EP 00 12 8267

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on  
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

02-06-2003


Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0008894      A	JP	55036296 A	13-03-1980
	JP	63051174 B	13-10-1988
	JP	1390886 C	23-07-1987
	JP	55048222 A	05-04-1980
	JP	61036781 B	20-08-1986
	JP	1650209 C	30-03-1992
	JP	3012094 B	19-02-1991
	JP	62089730 A	24-04-1987
	JP	1584173 C	22-10-1990
	JP	59074128 A	26-04-1984
	JP	62028169 B	18-06-1987
	JP	1594860 C	27-12-1990
	JP	2017571 B	20-04-1990
	JP	61043630 A	03-03-1986
	US	4273903 A	16-06-1981
	US	4268650 A	19-05-1981
	-----		

EPO FORM P/458


For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

in the formulae,  $R^2$  represents an alkyl group having 1 to 6 carbon atoms, an alkoxy group having 1 to 6 carbon atoms, a phenyl group or a phenoxy group, b is an integer from 0 to 4, and c is an integer from 0 to 6, and when a plurality of  $R^2$ s are present, these may be the same or different.

6. The polymer electrolyte according to Claim 1 or 2, wherein the blocks having sulfonic acid groups are blocks composed of an epoxy resin into which sulfonic acid groups have been introduced.
7. The polymer electrolyte according to Claim 6, wherein the blocks having sulfonic acid groups are blocks having a repeating unit represented by the general formula [3] into which sulfonic acid groups have been introduced:




in the formula [3],  $\text{Ar}^2$  represents a group selected from the following structures,



in the formulae,  $R^3$  represents an alkyl group having 1 to 6 carbon atoms, an alkoxy group having 1 to 6 carbon atoms or a phenyl group, d is an integer from 0 to 3, and e is an integer from 0 to 2; when a plurality of  $R^3$ s are present, these may be the same or different; Y represents -O-, -S-, an alkylene group having 1 to 20 carbon atoms, a halogenated alkylene group having 1 to 10 carbon atoms or an alkylenedioxy group having 1 to 20 carbon atoms; and when a plurality of Ys are present, these may be the same or different.

8. The polymer electrolyte according to Claim 1 or 2, wherein the blocks having substantially no sulfonic acid group are aromatic polyethers having a repeating unit represented by the general formula [4]:



in the formula,  $R^4$  represents an alkyl group having 1 to 6 carbon atoms; f is an integer from 0 to 4; when a plurality of  $R^4$ s are present, these may be the same or different; and Z represents -CO- or -SO<sub>2</sub>-.

9. The polymer electrolyte according to Claim 8, wherein Z is -SO<sub>2</sub>- in the general formula [4].
10. The polymer electrolyte according to Claim 1 or 2, wherein the amount of the block having substantially no sulfonic acid group is from 60 to 95% by weight based on the weight of the whole block copolymer.

11. A method for producing a polymer electrolyte of Claims 1 to 10, comprising the steps of: reacting a precursor of a block having repeating units represented by the general formula [1], [2] or [3], with a precursor of a block having a repeating unit represented by the general formula [4] to produce a block copolymer; and then sulfonating said copolymer.

12. The method for producing a polymer electrolyte according to Claim 11, wherein it comprises a step of sulfonating the block copolymer with sulfuric acid having a concentration of 90% or more.

13. A fuel cell obtainable by using a polymer electrolyte of any one of Claims 1 to 10.